

RAVAPROOF AVIPAST SPECIAL

Enriched bituminous emulsion



DESCRIPTION

RAVAPROOF AVIPAST SPECIAL is a water based bituminous emulsion in a pasty form. After maturation it makes an indissoluble coat that cannot be affected by dilute acid and alkaline solutions.

PRIMARY USES

Due to its excellent adhesion and its easy application, its suitable for protecting concrete substructures, brick constructions, floors, inclined roofs etc. and protection against moisture and humidity. It can also be combined with concrete and sand and latex bonding agent as to create a plastic mortar, with excellent mechanical resistance, which can be applied on industrial floors, gymnasium flooring, etc.

COMPOSITION

RAVAPROOF AVIPAST SPECIAL is produced by bitumen, in combination with special additives and water. It has a pasty form, and doesn't contain any solvent.

PACKAGING

RAVAPROOF AVIPAST SPECIAL is available in 5 and 18kg plastic containers and 220kg drums (upon request).

APPLICATION

The surface must be clean, free of oils, grease, and any residues, prior to use. It can be applied either on dry or slightly wet surfaces. **RAVAPROOF AVIPAST SPECIAL** must be applied at least twice on each surface, by bristle brush, roller or airless spray. For the first layer on Vertical Surfaces, thin out with 30-50% water. After the surface dries out, either thin out with ~20% of water or use it as it is and proceed on the second application. For the first layer on Horizontal Passable Surfaces, thin out with ~30% water. After the surface dries out proceed to the

application of each next coat either as it is or after dilution with a small amount of water. **RAVAPROOF AVIPAST SPECIAL** can be combined with glass paper or/and burlap, creating an in-situ bitumen fabric.

The material should not be applied at temperatures lower than 5°C and higher than 35 °C, in conditions of increased humidity, rainfall and potential rainfall or under direct sun exposition. Protect final layer with reflective paint such as RECTIFLEX.

TYPICAL PROPERTIES

Color	Brown-black
pH	8-9 (25°C)
Density (ASTM D 2939/98)	1050-1150 gr/L
Residue after evaporation (ASTM D 2939/98)	54-56 % w/w
Volatiles (ASTM D 2939/98)	44-46 % w/w
Ash content (ASTM D 2939/98)	≤28 % w/w
Water content (ASTM D 2939/98)	44-46 % w/w
Drying time (ASTM D 2939/98)	<24h
Resistance to heat at 100°C (ASTM D 2939/98)	No blistering, sagging or slipping
Resistance to water at 27°C for 24h(ASTM D 2939/98)	No blistering or reemulsification
Flexibility at 0°C (ASTM D 2939/98)	No cracking / peeling / loss of adhesion
Flexibility at -4°C (ASTM D 2939/98)	No cracking / peeling / loss of adhesion
Water absorption (EN 1062-3)	0,07 kg / m ² h
Adhesion (EN 1542)	1,7 N/mm ²
Permeability (EN ISO 7783)	51,3[S _D] (m)

ATHENS
Head Office
115, Neratziotissis str., Maroussi
15124, Athens, Greece
Tel.: +30 214 400 8 400

INOFYTA
Distribution Center
55th km National Road Athens-Lamia
32011, Inofyta, Viotia
Tel.: +30 22620 32 586

N.ARTAKI EVIA
Rooftile Plant
Profitis Ilias
34600, N.Artaki Evia
Tel.: +30 22210 43985

ARMA VIOTIAS
Bitumen Products Plant
Stathmos
32200, Arma Viotias
Tel.: +30 22620 72083

INOFYTA
Metal Profiles Plant
Thessi Kokkinoxoma
32011, Inofyta Viotias
Tel.: +30 22620 56214

Business Registered Number (GEMI): 363401000

Website: www.ravagohellas.gr

Email: info@ravagohellas.gr

RAVAPROOF AVIPAST SPECIAL

Enriched bituminous emulsion



CONSUMPTION

Consumption depends on the type of substrate and the characteristics of the intended use. Indicative for:

- Vapor Barrier: 0,6-0,8 kg/m² for each coat in 2 layers.
- Vertical Surfaces: Concrete or brick substructures protection 0,6-0,8 kg/m² in total. Watertight Coating: 1,5-2,5 kg/m² in total for multilayer application.
- Horizontal Surfaces: 2,0-3,0 kg/m² in total for water-proofing or 3,0-4,0 kg/m² for each coat is required when using reinforcement.

STORAGE

Use the product within two (2) years from the date of production. It should be stored indoors and at temperatures from 5-35°C. Close the package tightly after each use.

Storage under not recommended conditions will result in deterioration of the product or packaging.

SAFETY AND HEALTH

As with all chemicals, contact with eyes, mouth, skin and food should be avoided during use and storage. In case of contact with eyes and skin, use plenty of water and seek medical advice by referring label description and Safety Data Sheet. All used tools should be cleaned with water while the material is wet.

Seek medical attention immediately in case of contact with skin, eyes, or ingestion. Refer to the Safety Data Sheet for more information. The product is not classified as dangerous according to European Regulation 1272/2008.

Do not dispose of the material on the ground.

The information contained in this publication of RAVAGO HELLAS SA is believed to be accurate and provided in good faith, based on our current knowledge and experience, when the products are stored, used and applied under the prescribed conditions. Nevertheless is up to the Users to satisfy the suitability of the product for their own specific purpose.



ATHENS
Head Office
115, Neratziotissis str., Maroussi
15124, Athens, Greece
Tel.: +30 214 400 8 400

INOFYTA
Distribution Center
55th km National Road Athens-Lamia
32011, Inofyta, Viotia
Tel.: +30 22620 32 586

N.ARTAKI EVIA
Roofite Plant
Profitis Ilias
34600, N.Artaki Evia
Tel.: +30 22210 43985

ARMA VIOTIAS
Bitumen Products Plant
Stathmos
32200, Arma Viotias
Tel.: +30 22620 72083

INOFYTA
Metal Profiles Plant
Thessi Kokkinoxoma
32011, Inofyta Viotias
Tel.: +30 22620 56214

Business Registered Number (GEMI): 363401000

Website: www.ravagohellas.gr

Email: info@ravagohellas.gr