



Impact sound deadener



CelluCushion®5mm tech. information

Properties	Test Method	Unit	Value
Density	DIN 53420	Kg/m³	24
Thermal Conductivity	ASTM C-117	W/mk	0,055
Water Absorption (after 24 hr)	DIN 53428	Vol %	0,7
Fire resistance	DIN 4102	Class	B2
Working Temperature	Internal	°C	-30 up to +80
Impact sound insulation	ELOT 461.2	dB	55



Our products protects your products.®

CelluCushion® Impact sound deadener

Floating floor application.

