

RAVATHERM™ XPS LB (GV)

polystyrene extruded foam for the insulation of caravans and motorhomes with high compressive strength



- XPS Panels with butt edges, planed and grooved
- Versatile use
- Core material for caravans and motorhomes
- Tested and certified by FIW Institute Munich



Note: The recommendations regarding application methods and use of the products are based on the experience and knowledge of the properties of RAVATHERM™ insulation boards acquired by Ravago and are made to the best of our knowledge and belief. However, no liability, warranty, or guarantee is assumed for systems or applications. No exemption from patent claims can be derived from this. This document does not constitute a sales specification. The information in this brochure does not constitute a guarantee of properties in a legal sense and is not part of the content of a purchase agreement. Ravagos's obligations and liability regarding the sale of RAVATHERM™ products are determined exclusively by the underlying purchase agreement. <https://www.ravagobuildingsolutions.com/industry>

RAVATHERM™ XPS LB (GV)

Properties	Value		Unit	Norm	CE Code	
Density (typical value)	33		kg/m ³	EN 1602		
Thermal Conductivity Declared (λ_D)	0,033 0.034 0,035	≤ 60 mm > 60-100 mm > 100 mm	W/m.K	EN 13164	λ_D	
Thermal Conductivity for 60 days old foam – mean value at 10°C	–		W/m.K	EN 12667 EN 12939	λ -mean, 60d	
Compressive stress or compressive strength @ 10% deformation ¹	300		kPa	EN 826	CS(10\Y)	
Tensile Strength ¹	600		kPa	EN 1607	TR	
Shear strength ²	250		kPa	EN12090	SS	
Moduli (typical)	E-Modulus ¹	< 30 mm	MPa	EN 826		
		30-79 mm	MPa	EN 826		
		≥ 80 mm	MPa	EN 826		
	Tensile Modulus ¹	> 50 mm	MPa	EN 1607		
	Shear Modulus ²	7		MPa	EN 12090	
Compressive Creep max after 50 years < 2% deformation under stress σ_C	–		kPa	EN 1606	CC(2/1.5/50) σ	
Water vapour diffusion resistance factor μ (tabulated value)	150		-	EN 12086	MU	
Long term water absorption by total immersion	1.5		%	EN 12087	WL(T)	
Dimensional stability under specified temperature (70°C) and humidity conditions (90%rh)	< 5		%	EN 1604	DS(70,90)	
Deformation under specified compressive load (40kPa) and temperature (70°C) conditions	–			EN 1605	DLT(2)5	
Coefficient of linear thermal expansion (typical value)	0.07		mm/(m.K)	–	–	
Fire Performance	E		Euroclass	EN13501-1		
Temperature limits	-50/+75		°C	–		
Tolerances	Thickness	-0.5/+0.5	< 700 mm ≥ 700 mm	mm	EN 823	T
	Width	0.0/+3.0		mm	EN 822	
		0.0/+5.0		mm	EN 822	
Length	0.0/+10	mm	EN 822			
Dimensions	Thickness	20-122	mm	EN 823		
	Width	500-1211	mm	EN 822		
	Length	1700-4000	mm	EN 822		
Edge Profile	Butt Edge					
Surface finish	Planed					
	GV	Planed and grooved				

CE-code: **XPS - EN 13164 - T3 - CS(10\Y)300 - DS(70,90) - WL(T)1.5 - TR600 - SS250**

1 Measured in thickness direction

1 N/mm² = 10³ kPa = 1MPa

2 Typical value for Shear Modulus, may vary with the inplane direction

! The material must be stored in the original packaging and must not be exposed to direct sunlight or heat sources !