

Technical data sheet

Properties	Method	Unit	Values
Water tightness	BS EN 1928:2000 (A)	class	W1
Sd-value	BS EN ISO 12572:2016	m	0.01 (0.003 - 0.025)
Tensile force (MD)	BS EN 12311-1:2000	N/5cm	310 (280 - 340)
Elongation (MD)	BS EN 12311-1:2000	%	17.5 (15 - 20)
Tensile force (XD)	BS EN 12311-1:2000	N/5cm	310 (270 - 350)
Elongation (XD)	BS EN 12311-1:2000	%	20 (16 - 24)
Nail Shank (MD)	BS EN 12311-1:2000	N	50 (37 - 65)
Nail Shank (XD)	BS EN 12311-1:2000	N	45 (32 - 60)
Flexibility at low temperature	BS EN 1109:2013	-	-
Artificial aging by UV and heat:			
Tensile force (MD)	BS EN 12311-1:2000	%	85
Elongation (MD)	BS EN 12311-1:2000	%	75
Tensile force (XD)	BS EN 12311-1:2000	%	85
Elongation (XD)	BS EN 12311-1:2000	%	70
Water tightness	BS EN 1928:2000 (A)	class	W1
Width of roll	Length of roll	Weight per m²	Weight of roll
1,5 m	50 m	~ 63 g/m ²	~ 5 kg
3,0 m	100 m	~ 63 g/m ²	~ 19 kg

Material shall be stored inside in original packaging, away from direct sun light or heat sources

Note: The information and data contained in this technical data sheet do not represent exact sales specifications. The features of the products mentioned may vary. The information contained in this document has been provided in good faith, however it does not imply any liability, guarantee or assurance of product performance. It is the purchaser's responsibility to determine whether these products are suitable for the application desired and to ensure that the site of work and method of application conform with current legislation. No license is hereby granted for the use of patents or other industrial or intellectual property rights. If products are purchased, we advise following the most up-to-date suggestions and recommendations.